





# High Density Polyethylene SGE7252XP

### Description:

SGE7252XP is a bimodal high density polyethylene specially developed to manufacturing of caps and closures to beverages and soft drinks. This grade offers a good balance between chemical and mechanical resistance, good processability and organoleptic properties.

The minimum biobased content of this grade is 94%, determined according to ASTM D6866.

## Application:

Caps and closures for carbonated beverages.

#### Process:

Injection Molding.

#### Additives:

Slip Agent.

# **Control Properties:**

	Method	Units	Values
Melt Flow Rate (190/2.16)	ASTM D 1238	g/10 min	2.0
Density	ASTM D 792	g/cm <sup>3</sup>	0.952

# **Typical Properties:**

Plaque Properties<sup>a</sup>

	Method	Units	Values
Tensile Strength at Yield	ISO 527-2	MPa	26
Tensile Strength at Break	ISO 527-2	MPa	14
Elongation at Yield	ISO 527-2	%	9
Elongation at Break	ISO 527-2	%	400
Flexural Modulus	ISO 178	MPa	1200
Environmental Stress Cracking Resistance <sup>b</sup>	D 1693 B	h/F50	40
Full Notch Creep Test (FNCT)	Braskem method	h	≥ 24

<sup>(</sup>a) Test specimens prepared from compression molded sheet made according to ASTM D 4703.

#### **Final Remarks:**

- This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA Food and Drug Administration in force on the date of publication of this specification. The additives present are covered in appropriate regulation by FDA
- The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
- In some applications, Braskem has developed tailor-made resins to reach specific requirements.
- In case of doubt regarding utilization, or for other applications, please contact our Technical Assistance
- For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 25087-34-7. The mentioned values in this report can be changed at any moment without Braskem previous communication.
- Unless specified, Braskem does not recommend the use of this grade for the fabrication of packages, parts or any other type of product designed to medical and/or pharmaceutical applications.
- 8. The content of this Data Sheet replaces previous revisions published for this product.

<sup>(</sup>b) Compression molded 2 mm thickness, 0.3 mm notched-plaques; 10% Igepal; 50°C.